

Stimson Lumber Company

Sales and Marketing

520 SW Yamhill, Suite 700

Portland, OR 97204-1359

(503) 295-0951

(800) 445-9758

fax (503) 295-1849

TECHNICAL BULLETIN

1/8-Inch Stimson Hardboard

Specifications:

American National Standard

ANSI / AHA A135.4-1995 Basic Hardboard

Commercial Item Description

A-A-2243 Building Board, Hard Pressed Vegetable

Fiber (Hardboard)

International Conference of Building Officials


Evaluation Report No. 1300

Board Properties:

Weight	-	0.70 pounds per square foot
Density	-	59 pounds per cubic foot
Moisture Content	-	5-6 per cent
Caliper Range	-	as requested +/- 0.005 inch

ONE-EIGHTH INCH (1/8") STANDARD HARDBOARD meets the following average properties when tested in accordance with ASTM D 1037-95 Part B-Acceptance and Specification Test Methods for Hardboard.

	ANSI / AHA	
	Standard	Tempered
Water Absorption (%) (24 hour)	35	25
Thickness Swell (%) (24 hour)	25	20
Modulus of Rupture (PSI)	4,500	6,000
Internal Bond (PSI)	100	130



Stimson Lumber Company

Sales and Marketing

520 SW Yamhill, Suite 700
Portland, OR 97204-1359
(503) 295-0951
(800) 445-9758
fax (503) 295-1849

TECHNICAL BULLETIN

1/4-Inch Standard Hardboard

Specifications:

American National Standard
ANSI / AHA A135.4-1995 Basic Hardboard

Commercial Item Description
A-A-2243 Building Board, Hard Pressed Vegetable
Fiber (Hardboard)

International Conference of Building Officials
Evaluation Report No. 1300

Board Properties:

Weight	-	1.20 pounds per square foot
Density	-	59 pounds per cubic foot
Moisture Content	-	5-6 per cent
Caliper Range	-	as requested +/- 0.005 inch

ONE-EIGHTH INCH (1/4") STANDARD HARDBOARD meets the following average properties when tested in accordance with ASTM D 1037-95 Part B-Acceptance and Specification Test Methods for Hardboard.

	ANSI / AHA	
	Standard	Tempered
Water Absorption (%) (24 hour)	25	20
Thickness Swell (%) (24 hour)	20	15
Modulus of Rupture (PSI)	4,500	6,000
Internal Bond (PSI)	100	130